

# Tropical Breeze™ - Teal/Blue



**COVERSTOCK:** Reactor™ Pearl Reactive

**WEIGHT BLOCK:** Camber™ Core

**FACTORY FINISH:** 1500-grit Polished

**BALL COLOR:** Teal/Blue

**DUROMETER:** 74-76 Rex D-scale

**FLARE POTENTIAL:** 2" - 4" (Medium)

**FRAGRANCE:** Melon Mint

**WEIGHTS:** 10-16 lbs.

Lbs.	RG	Diff.	Weight Block
16	2.57	0.009	
15	2.57	0.009	
14	2.57	0.013	
13	2.63	0.009	
12	2.65	0.011	

## Resurfacing to a 1500-grit Polished Factory Finish

Resurface to the original factory finish using a ball spinner.

1. 500-grit Abralon® - Sand for 30 seconds on all four sides with firm pressure.
2. 1000-grit Abralon® - Sand for 20 seconds on all four sides with light pressure.
3. 2000-grit Abralon® - Sand for 20 seconds on all four sides with light pressure.
4. 4000-grit Abralon® - Sand for 20 seconds on all four sides with light pressure.
5. Storm Step Two™ - Polish lightly for 15 seconds each side.

**Storm recommends using the suggested cleaner/polish daily. Storm also recommends touching up the surface with only the final step every 20 games and resurfacing completely every 30-50 games.**

